

Grade	Application C-Commutator S-Slipping	Resistivity micro-ohm-cm	Transverse Strength Kgf/cm ²	Apparent Density gms/cc	Scleroscope Hardness shore	Contact drop Volt/brush	Current density Amps/cm ²	Coefficient of friction	Max. Operating speed	Pressure gf/cm ²	Application Guidance
LINK-B		2500	260	1.55	39	0.95	8.5	0.22	20	140 - 180	Graphite grade of high conductivity for machines presenting no commutation problem.